

# CSS CONNECXION

## Description:

### MASTER CSS ConnecXion

Mineral formulation designed to increase solids in cementitious surface, natural and composite stones with high resistance and less permeability properties.

## Characteristics

- *High Preservation Capabilities*
- *Extremely Durable*
- *Real-Time Drying*
- *Non-Darkening*
- *Non- Yellowing*

Treating and hardening all types of calcareous composition floor surfaces.

## Uses

Recommended for use on:

- Marble. Granite. Sandstones, Lime-Stone
- Terrazzo, Pebble Wash
- Cementitious surface

## Recommended Use

Show Room

Warehouse

Commercials Area

Office and many more

## Coverage:

Approximately 600- 1000 sq. ft. (60 - 100 m2)

1 gallon

**TEST A SMALL AREA, according to application instructions to determine desired results.**

## Caution:

- KEEP OUT OF REACH OF CHILDREN.
- INHALATION: Move to fresh air.
- IF INGESTED: Do not induce vomiting. Drink 1 to 2 glasses of water. Seek immediate medical attention.
- EYE CONTACT: Flush thoroughly with water for 15 minutes. If irritation persists, seek medical attention.
- SKIN CONTACT: Wash skin with soap and water. Remove contaminated clothing.

## Cementitious Surface

Excellence result on existing old concrete floor.

For new installations, recommend minimum 14 days or full cure.

## Method of application:

1. Read entire label before using.
2. TEST A SMALL AREA, according to application instructions to determine desired results.
3. Ensure surface is clean and dry.
4. Apply using roller CSS ConnecXion onto a manageable area of approximately 5 to 10 sq. ft. (0.5 m2 to 1 m2).
5. Using a synthetic fiber white pad, work the area in a side-to-side motion with a 175 to 300 RPM floor machine.
6. Ensure to overlap the sections to achieve an even penetrating of CSS ConnecXion.

## Polishing Cement/ Concrete Floor.

### For Polishing cement/ concrete floor

1. Concrete shall be at least 25n/mm2 compressive strength or higher.
2. Concrete must be cure a minimum of 28days prior to grinding and polishing.

Apply CSS Plasma or CSS Max

( Read Entire label before using ) as to achieve higher gloss result .

## Handling and storage:

- Close container tightly after each use.
- Store in original container only.
- Store and use between temperatures of 40 °F - 90 °F (4 °C - 32 °C).
- Dispose of residue or any unused leftover product in accordance with applicable federal, state, and local requirements.

## Ordering information:

**Package:** 1 us gallon / 3.785 liters

**Minimum:** one carton/ 4 X 1 us gallon

[www.master.co.th](http://www.master.co.th)

[www.cleanglobal.com](http://www.cleanglobal.com)

MASTER REFINISHING SYSTEMS (M) SDN BHD

Customer Support

Malaysia: +607 3511200 - +6012 7018890 – m\_shchin@yahoo.com

Thailand: (66)02- 791-3845 - 086-068-2-333 - [tstan@truemail.co.th](mailto:tstan@truemail.co.th)

Middle East: +966 05680 61137 - +2010 1618 125 - [mastermiddleeast@live.com](mailto:mastermiddleeast@live.com)